

## Tolerances for flat drawn bars - SEC UNI EN 10278

### Tolleranze per i piatti trafilati - acc UNI EN 10278

on WIDTH	TOLERANCE	
Sulla LARGHEZZA	TOLLERANZA	
mm	mm	mm
≤ 18	+0	-0.11
> 18 ≤ 30	+0	-0.13
> 30 ≤ 50	+0	-0.16
> 50 ≤ 80	+0	-0.19
> 80 ≤ 100	+0	-0.22
> 100 ≤ 150 (*)	+0.50	-0.50
> 150 ≤ 200	+1.00	-1.00
> 200 ≤ 300	+2.00	-2.00
> 300 ≤ 400	+2.50	-2.50

on THICKNESS	TOLERANCE	
Sullo SPESSORE	TOLLERANZA	
mm	mm	mm
> 3 ≤ 6	+0	-0.075
> 6 ≤ 10	+0	-0.090
> 10 ≤ 18	+0	-0.11
> 18 ≤ 30	+0	-0.13
> 30 ≤ 50	+0	-0.16
> 50 ≤ 60	+0	-0.19
> 60 ≤ 80	+0	-0.30
> 80 ≤ 100	+0	-0.35

(\*) in deroga alla norma EN 10278, possiamo fornire tolleranza h11 anche nel range di spessori 100÷140 mm (+0/-0,22 mm)

(\*) derogating norm EN 10278, we can provide tolerance h.11 also within the range of thicknesses 100÷140 mm (+0/-0,22 mm)

Sulla LUNGHEZZA/ on length: mm. 3000: – 0/+10%

mm. 6000: – 0/+10%

lunghezze fisse a richiesta -fixed lengths upon request.